



## AVAILABLE SS-EZCOAT COLORS:



115 Grey



134 Light Grey



680 Yellow



750 Tan

## SS-EZCoat Pigment amounts and mixing instructions

### SS-EZCoat Standard pigment pack colors

SureCoat Systems pigment packs are packaged in quart cans. The amount of pigment required per gallon is pre-packaged in the quart cans. The pigment is added directly to the SS-EZCoat clear coat and hand mixed, or slowly blended with a power mixer.

The amount of pigment required by color is listed below.

### PIGMENT AMOUNTS BY COLOR:

<b>Tan:</b>	2.0 pounds of pigment per gallon
<b>Grey:</b>	2.0 pounds of pigment per gallon
<b>Yellow:</b>	3.0 pounds of pigment per gallon
<b>Light grey:</b>	3.0 pounds of pigment per gallon



## SS-EZCOAT SINGLE COMPONENT FLOOR COATING PIGMENT

SureCoat Systems pigment dispersions have been formulated in polyether polyol, and are used to color our SS-EZCOAT. STORAGE: Containers should be sealed when not in use and kept free of moisture or debris. Material should be mixed thoroughly before use. Shelf life from the date of manufacture is 12 months.

### TECHNICAL DATA

#### PHYSICAL PROPERTIES

CARRIER polyether polyol

SS-EZCOAT PIGMENT VOC 50 gm/liter

Curing (each coat) when mixed with SS-EZCOAT 2-6 hours

Code	Color Pigment	Pigment %	Carrier %	Lbs per gal
112	Grey	42%	58%	12
134	Lt Grey	45%	55%	12
750	Tan	46%	54%	12
680	Yellow	10%	90%	12

Notice: Our technical advice, whether given verbally or in writing, is given in good faith but without warranty. It is the customer's obligation to test the products supplied by us for their suitability for the intended application. The application, use and processing of the products are beyond our control, and are the customer's responsibility. Should liability be established for any damage, it will be limited to the value of the goods delivered by us, and used by the customer. We promise to provide products of consistent quality.